

## CIRCULUM®

---

### G-710e/p

---

#### DESCRIPTION

**G-710e/p** is an expandable polystyrene grade with reduced thermal conductivity containing graphite. Pentane is used as a blowing agent. The product is delivered in the form of non-spherical beads with a bulk density of about 0,6 g/cm<sup>3</sup> and is available in 1100 kg octabins (G-710p) and 1050 kg octabins (G-710e).

**G-710e/p** contains at least 10% rGPPS (recycled polystyrene).

#### APPLICATIONS

The properties of **G-710e/p** make it suitable for the production of thick-walled shape-moulded products as well as heavy insulation board by continuous machine or block process.

#### PROCESSING

The processing conditions of **G-710e/p** depend on the combination of the product and processing equipment used. Optimal settings have to be adjusted for each combination. Some general processing conditions are given below:

<b>Prefoaming</b>	The steam has to be saturated at a temperature of 100 - 110 °C. To reach higher densities (> 30 kg/m <sup>3</sup> ) it is recommended to mix the steam with air.
<b>Conditioning</b>	Depends on the density, generally 12 - 24 hours is recommended.
<b>Moulding</b>	The machine should be fed with saturated steam with a max pressure of about 2 bar. Steaming time depends on the equipment used as well as the size and required strength of the final product. Therefore, all machines have to be adjusted individually. Equipment using vacuum is recommended to reduce cycle times and to increase product strength.
<b>Cutting</b>	Hot wire cutting - oscillating or stationary wires - is recommended. Temperature of the wires should be about 200 - 300 °C.

---

---

### TECHNICAL INFORMATION

---

#### TYPICAL PHYSICAL PROPERTIES

Raw material	Value	Unit	Test method
Pentane content	4.5-5.5	%	Gas chromatography
Monomer level	< 0.1	%	Gas chromatography
Main bead size distribution	0.7 – 1.1	mm	Image analyser

#### STORAGE AND HANDLING

**G-710e/p** should be stored below 20 °C. Avoid direct sunlight and keep away from any source of ignition. To ensure the best performance in prefoaming and moulding, the storage time should not exceed one month.

#### SAFETY

**G-710e/p** is not classified as a dangerous material. A Safety Data Sheet is available on request.

Avoid generating dust. All equipment should be properly grounded. Releases pentane during processing, which might form a flammable/explosive vapour - air mixture. Use proper ventilation.

#### RECYCLING

**G-710e/p** is suitable for recycling using modern methods of grinding, cleaning and regranulating. In-house production waste should be kept clean to facilitate direct recycling. Please contact your BEWI RAW representative for more details on various aspects of safety, recovery and disposal of the product.

---

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with a customer.

La présente documentation n'engage pas notre responsabilité et n'autorise en aucune façon l'usage sans contrat de licence d'inventions brevetées. Les termes du présent rapport doivent être considérés comme une simple indication, sujette aux vérifications d'usage.

Bei diesen Angaben handelt es sich weder um eine Garantie-Erklärung oder Darstellung, für die wir eine rechtliche Haftung übernehmen, noch um eine Erlaubnis oder Empfehlung, irgendeine patentierte Erfindung ohne Lizenz auszuwerten. Die Informationen werden Ihnen lediglich zu Ihrer Erwägung, Untersuchung und Überprüfung übermittelt und sind nicht Bestandteil von Verträgen mit Kunden.

Uppgifter i datablad, broschyrer och annat informationsmaterial ges som vägledning och är ej bindande för BEWI RAW.

Tässä esitteessä ja muussa tiedotusaineistossa annetut tekniset tiedot ovat suuntaa antavia, eivätkä ne ole BEWI RAW sitovia.

Le informazioni contenute nelle schede tecniche, bollettini ed altro materiale informativo corrispondono all'attuale livello di conoscenza e intendono fornire indicazioni sui prodotti BEWI RAW e le loro possibilità di impiego. Non sono pertanto da intendersi come garanzia. lita' di impiego.